

Rubber profiles

Fender profiles

VRTRADE



MECHANICAL	Standard	Value	
Rubber compound		EPDM	
Density	ASTM D3575	1.25 +/-0.05	g/cm3
Hardness	ASTM D2240	70 ⁰ +/-5	Shore A
Tensile strength	ISO 37	8	MPa
Elongation at break	ISO 37	≥ 350	%
Tear resistance		60	N/mm
Compression set after 24h at 70 ⁰ C		40	%
Tollerances according to	DIN ISO 3302-1	E2	
Country of origin		Italy	
TEMPERATURE			
Working temperature		-40 ⁰ C - +100 ⁰ C	
CHEMICAL RESISTANCE			
Diluted acids and bases		Moderate	
Concentrated acids and basis		Non suitable	
Ozone and UV		Excellent	
Oils and hydrocarbons		Non suitable	