


# Switchboardmatting Class 2

**VRTRADE**



MECHANICAL		Standard	Value		Test Method
Rubber compound			SBR		
Density	ASTM D397	1.60 +/-0.05	g/cm <sup>3</sup>		ASTM D397
Hardness	ASTM D2240	65 <sup>0</sup> +/-5	Shore A		ASTM D2240
Tensile strength	ASTM D412	4	MPa		ASTM D412
Elongation at break	ASTM D412	200	%		ASTM D412
Tear resistance					
Compression set after 24h at 70°C					
TEMPERATURE					
Working temperature		-30°C - +90°C			
CERTIFIED					
According to	IEC 61111:2009 / DIN EN 60243-1				
Working Voltage	17.000 V				
Proof Voltage	20.000 V				
Withstand Voltage	30.000V				
DIMENSIONS					
SKU	Thickness (mm)	Width (mm)	Length (m)	Colour	Execution
VR30104970HT	4	1000	10	grey	small ribbed top
VR30104980HT	4	1200	10	grey	small ribbed top